

SID

Factory: Rot am See

Article:

644

ML4

Provided:

Stockburger, Olesja

Customer:

Date:

20.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	550		2
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		3
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		4
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	165		5
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		6
C-RS-FR4-DS-1.55mm-105+105-TG150-HF	50201125	105	L2	7
		1340		
		105	L3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	165		8
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		9
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	550		10
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		11
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		12
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	13

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

3120 µm

Version 1.2.14.15

© Würth Elektronik